



US005993543A

United States Patent [19]

Aoki et al.

[11] Patent Number: 5,993,543

[45] Date of Patent: Nov. 30, 1999

[54] METHOD OF PRODUCING PLASMA
DISPLAY PANEL WITH PROTECTIVE
LAYER OF AN ALKALINE EARTH OXIDE

[75] Inventors: Masaki Aoki, Mino; Hideo Torii,
Higashiosaka; Eiji Fujii, Hirakata;
Mitsuhiro Ohtani, Sakai; Takashi
Inami, Suita; Hiroyuki Kawamura,
Katano; Hiroyoshi Tanaka, Kyoto;
Ryuichi Mural, Toyonaka; Yasuhisa
Ishikura, Katano; Yutaka Nishimura,
Kadoma; Katsuyoshi Yamashita,
Katano, all of Japan

[73] Assignee: Masaki Aoki Et Al., Japan

[21] Appl. No.: 08/890,577

[22] Filed: Jul. 9, 1997

Related U.S. Application Data

[62] Division of application No. 08/766,030, Dec. 16, 1996, Pat.
No. 5,770,921.

[30] Foreign Application Priority Data

Dec. 15, 1995	[JP]	Japan	7-326766
Feb. 1, 1996	[JP]	Japan	8-016326
Jun. 24, 1996	[JP]	Japan	8-162639
Aug. 26, 1996	[JP]	Japan	8-223428

[51] Int. Cl.⁶ C30B 29/16; C30B 23/00

[52] U.S. Cl. 117/88; 117/101; 117/103;
117/104; 117/944

[58] Field of Search 117/3, 88, 92,
117/101, 103, 104, 944; 313/572, 581,
582

[56] References Cited

U.S. PATENT DOCUMENTS

4,198,585	4/1980	Yamashita et al.	313/587
4,584,086	4/1986	Hayakawa et al.	204/429
5,458,086	10/1995	Smith et al.	117/200
5,604,396	2/1997	Watanabe et al.	313/485
5,818,168	10/1998	Ushifusa et al.	313/582
5,844,362	12/1998	Tanabe et al.	313/506

FOREIGN PATENT DOCUMENTS

279744	8/1988	European Pat. Off. .
649159	4/1995	European Pat. Off. .
5234519	10/1993	Japan .
5342991	12/1993	Japan .
6342631	12/1994	Japan .
2109628	6/1983	United Kingdom .
9519027	7/1995	WIPO .

OTHER PUBLICATIONS

"E-Beam Evaporated Glass and MgO Layers for Gas Panel
Fabrication," by K.C. Park et al., IBM J. Res. Develop., vol.
22, No. 6, Nov. 1978.

"Fluorescent Substance for Color Plasma Display Panel," by
J. Koike, O Plus E, No. 195, 1996.

"Low-Voltage Operated AC Plasma-Display Panels", by T.
Shinoda et al., IEEE Transactions on Electron Devices, vol.
ED-26, No. 8, Aug. 1979.

Primary Examiner—Felisa Hitesher

Assistant Examiner—Donald L. Champagne

Attorney, Agent, or Firm—Price, Gess & Ubell

[57] ABSTRACT

The first object of the present invention is to provide a PDP with improved panel brightness which is achieved by improving the efficiency in conversion from discharge energy to visible rays. The second object of the present invention is to provide a PDP with improved panel life which is achieved by improving the protecting layer protecting the dielectrics glass layer. To achieve the first object, the present invention sets the amount of xenon in the discharge gas to the range of 10% by volume to less than 100% by volume, and sets the charging pressure for the discharge gas to the range of 500 to 760 Torr which is higher than conventional charging pressures. With such construction, the panel brightness increases. Also, to achieve the second object, the present invention has, on the surface of the dielectric glass layer, a protecting layer consisting of an alkaline earth oxide with (100)-face or (110)-face orientation. The protecting layer, which may be formed by using thermal Chemical Vapor Deposition (CVD) method, plasma enhanced CVD method, or a vapor deposition method with irradiation of ion or electron beam, will have a high sputtering resistance and effectively protect the dielectrics glass layer. Such a protecting layer contributes to the improvement of the panel life.

27 Claims, 9 Drawing Sheets

